

The following proposed revision items are recommended by the Supervisors:

**Section 403.01 shall be revised as follows:**

The ballast material shall be run through a crushing plant. Material that has only been screened will not be accepted. The ballast shall be placed to a minimum of 12-inches in thickness. The material shall be durable, have a sand equivalent not less than 30, and shall meet the following gradations:

Sieve Size	Ballast % Passing
4"	100
3"	98-100
2"	90-100
3/4"	70-90
#4	25-40
#200	3-9

Ballast material will be used at the direction of the Highway District. Material shall be basalt or crushed prairie gravel with one or more fractured faces or natural angular faces on 75 percent of the particles retained on the #4 sieve or above as determined by Idaho T-71 test.

**END ADDEDNDUM**